



AEROSPEC 250

Extreme low temperature, molybdenum disulphide aerospace grease. Designed to give outstanding operational performance on a wide range of airframe components including splines, sliding surfaces and anti-friction bearings where high loads are encountered.

FEATURES

- Ø Temperature range -75°C to 120°C
- Ø Excellent low temperature performance
- Ø Wide operating temperature range
- Ø Exceptional stability
- Ø Highly resistant to water washout
- Ø Approved to: DEF STAN 91-57/2, JSD XG 276

DIRECTIONS FOR USE

- Ø Ensure all components are clean and free from any contaminants.
- Ø It is recommended that previous lubricants be cleaned out of the equipment prior to filling with Aerospec 250.
- Ø Apply manually or by using an applicator suitable for NLGI No.2 greases

Technical and Safety Data Sheets are available from:

Fax Back Facility : +44 (0)113 232 2770
Web Site : www.rocol.com
Customer Service : +44 (0) 113 232 2700

Issue 06520e: Jan-04

ROCOL Lubricants

ROCOL House, Swillington, Leeds LS26 8BS, England.

Tel: +44 (0) 113 232 2600 Fax: +44 (0) 113 232 2760

www.rocol.com

ROCOL is a BS EN ISO 9001 registered company.

ROCOL is a trade mark of ITW Inc.

The information in this publication is based on our experience and reports from customers. There are many factors outside our control or knowledge which affect the use and performance of our products, for which reason it is given without responsibility.



AEROSPEC 250

TECHNICAL DATA (typical values)

Appearance	Smooth blue/black grease
Base fluid type	Synthetic
Viscosity at 40 ⁰ C (IP71)	8.6 cSt
Viscosity at 100 ⁰ C (IP71)	2.5 cSt
Lubricating solids	Molybdenum disulphide
Thickener	Lithium complex soap
NLGI No. (IP 50)(ASTM D217)	NLGI No. 2
Temperature range	-75 ⁰ C to 120 ⁰ C
Drop point (IP 396)	>200 ⁰ C
Copper corrosion (IP 112)	Pass (24 hours at 100 ⁰ C)
Emcor rating (IP 220)	0 : 0
Low temp. torque test (IP 186) -73 ⁰ C	
Starting torque	190 mNm
Running torque	130 mNm
Shelf life	3 years
Storage	Storage temperature should be controlled to between 1 and 40 °C.
Pack sizes	125 g, 3 kg

Issue 06520e: Jan-04

2

ROCOL Lubricants

ROCOL House, Swillington, Leeds LS26 8BS, England.

Tel: +44 (0) 113 232 2600 Fax: +44 (0) 113 232 2760

www.rocol.com

ROCOL is a BS EN ISO 9001 registered company.

ROCOL is a trade mark of ITW Inc.

The information in this publication is based on our experience and reports from customers. There are many factors outside our control or knowledge which affect the use and performance of our products, for which reason it is given without responsibility.

TECHNICAL DATA