



# FOODLUBE UNIVERSAL 000

**Food grade semi-fluid EP grease fortified with PTFE.  
Non-toxic lubricant designed for the effective lubrication and protection  
of ball, roller and plain bearings operating in food/clean environments.**

## FEATURES

- Ø Temperature range  $-50^{\circ}\text{C}$  to  $160^{\circ}\text{C}$
- Ø Outstanding EP performance (400kg weld load)
- Ø Highly resistant to water wash off
- Ø Designed for use in centralised, multiline, lubrication systems
- Ø Excellent corrosion protection
- Ø Does not contain: mineral hydrocarbons, animal derived materials, nut oils or genetically modified ingredients.
- Ø FDA Group 21 CFR 178.3570
- Ø NSF H1 registered – 122068
- Ø DIN V 10517

## DIRECTIONS FOR USE

- Ø Fill reservoirs to the level recommended by the system manufacturer.
- Ø Compatible with other soap thickened greases. However, for best results, the previous lubricant should be removed prior to application.

### Technical and Safety Data Sheets are available from:

**Fax Back Facility** : +44 (0)113 232 2770  
**Web Site** : [www.rocol.com](http://www.rocol.com)  
**Customer Service** : +44 (0)113 232 2700

Issue 15286d: Jan-04

### **ROCOL Lubricants**

ROCOL House, Swillington, Leeds LS26 8BS, England.

Tel: +44 (0)113 232 2600 Fax: +44 (0)113 232 2760

[www.rocol.com](http://www.rocol.com)

ROCOL is a BS EN ISO 9001 registered company.

ROCOL is a trade mark of ITW Inc.

The information in this publication is based on our experience and reports from customers.  
There are many factors outside our control or knowledge which affect the use and performance  
of our products, for which reason it is given without responsibility.

T  
E  
C  
H  
N  
I  
C  
A  
L  
  
D  
A  
T  
A



# FOODLUBE UNIVERSAL 000

## TECHNICAL DATA (typical values)

Appearance	White, semi-fluid grease
NLGI No. (IP 50)(ASTM D217)	NLGI No. 000
Base type	Polyalphaolefin
Thickener	Aluminium complex soap
Solids	HLWS/PTFE
Temperature range	-50 <sup>0</sup> C to 160 <sup>0</sup> C
Base fluid viscosity at 40 <sup>0</sup> C	47 cSt
Shell 4 ball (IP 239)(ASTM D2596)	
Weld load	400 kg
Copper corrosion test (IP 112)(ASTM D130)	Pass
Storage	Storage temperature should be controlled to between 1 and 40 °C.
Pack sizes	4kg, 18kg

Issue 15286d: Jan-04

2

### ROCOL Lubricants

ROCOL House, Swillington, Leeds LS26 8BS, England.

Tel: +44 (0)113 232 2600 Fax: +44 (0)113 232 2760

[www.rocol.com](http://www.rocol.com)

ROCOL is a BS EN ISO 9001 registered company.

ROCOL is a trade mark of ITW Inc.

The information in this publication is based on our experience and reports from customers. There are many factors outside our control or knowledge which affect the use and performance of our products, for which reason it is given without responsibility.

TECHNICAL DATA