



FOODLUBE UNIVERSAL 2

**Food grade multipurpose EP grease fortified with PTFE.
Non-toxic lubricant designed for the effective lubrication and protection
of ball, roller and plain bearings operating in food/clean environments.**

FEATURES

- Ø Temperature range -50°C to 160°C
- Ø Outstanding EP performance (620kg weld load)
- Ø Highly resistant to water wash off
- Ø Suitable for use in electrical motors and fans
- Ø Excellent corrosion protection
- Ø Does not contain: mineral hydrocarbons, animal derived materials, nut oils or genetically modified ingredients.
- Ø FDA Group 21 CFR 178.3570
- Ø NSF H1 registered – 121603
- Ø DIN V 10517

DIRECTIONS FOR USE

- Ø Apply manually or with a suitable applicator e.g. ROCOL grease gun
- Ø Compatible with other soap thickened greases. However, for best results, the previous lubricant should be removed prior to application.

Technical and Safety Data Sheets are available from:

Fax Back Facility : +44 (0)113 232 2770
Web Site : www.rocol.com
Customer Service : +44 (0)113 232 2700

Issue 15231g: Jan-04

ROCOL Lubricants

ROCOL House, Swillington, Leeds LS26 8BS, England.

Tel: +44 (0)113 232 2600 Fax: +44 (0)113 232 2760

www.rocol.com

ROCOL is a BS EN ISO 9001 registered company.

ROCOL is a trade mark of ITW Inc.

The information in this publication is based on our experience and reports from customers. There are many factors outside our control or knowledge which affect the use and performance of our products, for which reason it is given without responsibility.

T
E
C
H
N
I
C
A
L

D
A
T
A



FOODLUBE UNIVERSAL 2

TECHNICAL DATA (typical values)

Appearance	White, tenacious grease
NLGI No. (IP 50)(ASTM D217)	NLGI No. 2
Base type	Polyalphaolefin
Thickener	Aluminium complex soap
Solids	HLWS/PTFE
Temperature range	-50 ⁰ C to 160 ⁰ C
Drop point	>230 ⁰ C
Base fluid viscosity at 40 ⁰ C	47 cSt
Base fluid viscosity at 100 ⁰ C	8 cSt
Shell 4 ball (IP 239)(ASTM D2596)	
Weld load	620 kg
SKF Rof Bearing Life	1100 Hours
Copper corrosion test (IP 112)(ASTM D130)	Pass
Water washout test (IP 215)(ASTM D 1264)	<2.0%
Storage	Storage temperature should be controlled to between 1 and 40 °C.
Pack sizes	380g cart, 4kg, 18 kg

Issue 15231g: Jan-04

2

ROCOL Lubricants

ROCOL House, Swillington, Leeds LS26 8BS, England.

Tel: +44 (0)113 232 2600 Fax: +44 (0)113 232 2760

www.rocol.com

ROCOL is a BS EN ISO 9001 registered company.

ROCOL is a trade mark of ITW Inc.

The information in this publication is based on our experience and reports from customers. There are many factors outside our control or knowledge which affect the use and performance of our products, for which reason it is given without responsibility.

TECHNICAL DATA