



# FOLIAC GRAPHITED P.J.C.

**Setting pipe sealant for metallic threaded and flanged joints  
Primarily for High Pressure Steam, Air & Water**

## FEATURES

- Ø Temperature range  $-20^{\circ}\text{C}$  to  $450^{\circ}\text{C}$
- Ø Suitable for pressures up to 1400 psi (97 bar)
- Ø Pressure test after a minimum 24 hours
- Ø Sets semi-hard but flexible
- Ø Resists vibration and thermal expansion
- Ø Easy to break and clean joints

## DIRECTIONS FOR USE

- Ø Do not apply in sub-zero temperatures
- Ø Ensure surfaces are clean and free of contaminants. Apply by brush
- Ø Assemble within 5 minutes
- Ø Pressure test after a minimum of 24 hours at ambient ( $20-25^{\circ}\text{C}$ )
- Ø Lower temperatures will extend drying time

### Technical and Safety Data Sheets are available from:

**Fax Back Facility** : +44 (0)113 232 2770  
**Web Site** : [www.rocol.com](http://www.rocol.com)  
**Customer Service** : +44 (0)113 232 2700

Issue 30022b: Jan-04

### **ROCOL Lubricants**

ROCOL House, Swillington, Leeds LS26 8BS, England.

Tel: +44 (0)113 232 2600 Fax: +44 (0)113 232 2760

[www.rocol.com](http://www.rocol.com)

ROCOL is a BS EN ISO 9001 registered company.

ROCOL is a trade mark of ITW Inc.

The information in this publication is based on our experience and reports from customers.  
There are many factors outside our control or knowledge which affect the use and performance  
of our products, for which reason it is given without responsibility.

T  
E  
C  
H  
N  
I  
C  
A  
L  
  
D  
A  
T  
A



# FOLIAC GRAPHITED P.J.C.

## TECHNICAL DATA (typical values)

Appearance	Grey compound
Unworked penetration at 25°C	260 - 310
Base type	Vegetable oil
Solids	Graphite
Temperature range	-20°C to 450°C
Pressure	Up to 1400 psi (97 bar)
Suitable applications	Steam Air Water Natural gas
Storage	Storage temperature should be controlled to between 1 and 40 °C.
Pack sizes	375g

Issue 30022b: Jan-04

2

### **ROCOL Lubricants**

ROCOL House, Swillington, Leeds LS26 8BS, England.

Tel: +44 (0)113 232 2600 Fax: +44 (0)113 232 2760

[www.rocol.com](http://www.rocol.com)

ROCOL is a BS EN ISO 9001 registered company.

ROCOL is a trade mark of ITW Inc.

The information in this publication is based on our experience and reports from customers. There are many factors outside our control or knowledge which affect the use and performance of our products, for which reason it is given without responsibility.

TECHNICAL DATA