



OILSEAL

**Setting pipe sealant for metallic threaded and flanged joints
Primarily for Mineral Oils, Petrol, Diesel, Fuel Oils, White Spirit & Paraffin**

FEATURES

- Ø Temperature range -50°C to 200°C
- Ø Suitable for pressures up to 2000 psi (138 bar)
- Ø Sets hard but flexible
- Ø Resists vibration and thermal expansion

DIRECTIONS FOR USE

- Ø Do not apply in sub-zero temperatures
- Ø Check sealing performance with Stainless Steel before use
- Ø Ensure surfaces are clean and free of contaminants
- Ø Stir thoroughly before and during use
- Ø Apply with a brush and assemble as in normal practice
- Ø Allow up to 6 hours for sealant to cure before pressure testing
- Ø Curing time should be extended when applying below 20°C

Technical and Safety Data Sheets are available from:

Fax Back Facility : +44 (0)113 232 2770
Web Site : www.rocol.com
Customer Service : +44 (0)113 232 2700

Issue 28032b – May-04

ROCOL Lubricants

ROCOL House, Swillington, Leeds LS26 8BS, England.

Tel: +44 (0)113 232 2600 Fax: +44 (0)113 232 2760

www.rocol.com

ROCOL is a BS EN ISO 9001 registered company.

ROCOL is a trade mark of ITW Inc.

The information in this publication is based on our experience and reports from customers.
There are many factors outside our control or knowledge which affect the use and performance
of our products, for which reason it is given without responsibility.



OILSEAL

TECHNICAL DATA (typical values)

Appearance	Thixotropic white liquid
Base type	Organic resin & alcoholic solvent
Solids	Clay
Temperature range	-50 ⁰ C to 200 ⁰ C
Pressure	Up to 2000 psi (138 bar)
Suitable applications	Mineral Oils Vegetable Oils Petrol, Diesel & Fuel Oils Paraffin & White Spirit Liquefied Petroleum Gas (LPG)
Compatibility	Check sealing performance when using with Stainless Steels
Storage	Store in a cool, well-ventilated area. Keep away from sources of ignition. Keep container tightly closed.
Pack sizes	300g

Issue 28032b – May-04

2

ROCOL Lubricants

ROCOL House, Swillington, Leeds LS26 8BS, England.

Tel: +44 (0)113 232 2600 Fax: +44 (0)113 232 2760

www.rocol.com

ROCOL is a BS EN ISO 9001 registered company.

ROCOL is a trade mark of ITW Inc.

The information in this publication is based on our experience and reports from customers. There are many factors outside our control or knowledge which affect the use and performance of our products, for which reason it is given without responsibility.

TECHNICAL DATA