



PIPESEAL PTFE LIQUID

**Flexible, setting pipe sealant for metallic threaded joints
Primarily for Air, Water & Steam**

FEATURES

- Ø Temperature range -50°C to 250°C
- Ø Suitable for pressures up to 400 psi (28 bar)
- Ø Only use where good mechanical sealing exists
- Ø Pressure test after a minimum of 6 hours
- Ø Sets hard but flexible
- Ø Resists thermal expansion
- Ø Can replace PTFE thread tape in many applications

DIRECTIONS FOR USE

- Ø Do not apply in sub-zero temperatures
- Ø Shake well before use
- Ø Ensure surfaces are clean and free of contaminants
- Ø Apply with a brush to both surfaces
- Ø Assemble within 5 minutes
- Ø Pressure test after a minimum of 6 hours at ambient ($20-25^{\circ}\text{C}$)
- Ø Lower temperatures will extend drying time

Technical and Safety Data Sheets are available from:

Fax Back Facility : +44 (0)113 232 2770

Web Site : www.rocol.com

Customer Service : +44 (0)113 232 2700

Issue 28022b: Jan-04

ROCOL Lubricants

ROCOL House, Swillington, Leeds LS26 8BS, England.

Tel: +44 (0)113 232 2600 Fax: +44 (0)113 232 2760

www.rocol.com

ROCOL is a BS EN ISO 9001 registered company.

ROCOL is a trade mark of ITW Inc.

The information in this publication is based on our experience and reports from customers.
There are many factors outside our control or knowledge which affect the use and performance
of our products, for which reason it is given without responsibility.



PIPESEAL PTFE LIQUID

TECHNICAL DATA (typical values)

Appearance	White emulsion
Base type	Organic resin & solvent
Solids	PTFE
Temperature	-50°C to 250°C
Pressure	Up to 400 psi (28 bar)
Suitable applications	Air Water Steam Mineral & Vegetable oils Paraffin & White Spirit Ammonia refrigerant LPG & Natural gas
Storage	Store away from sources of heat or ignition. Storage area should be: well ventilated. under cover. Storage and transfer equipment should be adequately earthed and bonded to prevent the accumulation of static charges.
Pack sizes	300g

Issue 28022b: Jan-04

2

ROCOL Lubricants

ROCOL House, Swillington, Leeds LS26 8BS, England.

Tel: +44 (0)113 232 2600 Fax: +44 (0)113 232 2760

www.rocol.com

ROCOL is a BS EN ISO 9001 registered company.

ROCOL is a trade mark of ITW Inc.

The information in this publication is based on our experience and reports from customers. There are many factors outside our control or knowledge which affect the use and performance of our products, for which reason it is given without responsibility.

TECHNICAL DATA