



# SAPPHIRE PRECISION LUBE SPRAY

High performance maintenance lubricant with PTFE. Designed to provide excellent lubrication, penetration and protection in the widest range of applications. It is clean, non-toxic, highly penetrating and free from chlorinated solvents. Reduces friction in all moving parts including chains, threaded components, sliding surfaces etc...

## FEATURES

- Ø Temperature range  $-55^{\circ}\text{C}$  to  $250^{\circ}\text{C}$
- Ø Outstanding EP performance (315kg weld load)
- Ø Ultra high performance universal maintenance lubricant
- Ø Clean non-toxic lubricating film
- Ø Contains PTFE as a solid lubricant - reduces friction

## DIRECTIONS FOR USE

- Ø Shake aerosol well before use
- Ø Apply from a distance of 15-30cm (6-12 inches)
- Ø ROCOL SAPPHIRE PRECISION LUBE can be sprayed from any angle due to  $360^{\circ}$  valve technology, enabling easy application of the product
- Ø It is recommended that compatibility with painted and coated surfaces, plastics and rubbers be tested prior to use.

### Technical and Safety Data Sheets are available from:

**Fax Back Facility** : +44 (0)113 232 2770  
**Web Site** : [www.ocol.com](http://www.ocol.com)  
**Customer Service** : +44 (0)113 232 2700

Issue 34341c: Jan-04

1

### **ROCOL Lubricants**

ROCOL House, Swillington, Leeds LS26 8BS, England.

Tel: +44 (0)113 232 2600 Fax: +44 (0)113 232 2760

[www.ocol.com](http://www.ocol.com)

ROCOL is a BS EN ISO 9001 registered company.

ROCOL is a trade mark of ITW Inc.

The information in this publication is based on our experience and reports from customers. There are many factors outside our control or knowledge which affect the use and performance of our products, for which reason it is given without responsibility.

TECHNICAL DATA



# SAPPHIRE PRECISION LUBE SPRAY

## TECHNICAL DATA (typical values)

Appearance	Almost colourless liquid
Base type	Synthetic ester containing EP and anti-wear additives
Solvent	Hydrocarbon
Propellant	LPG (Hydrocarbon)
Solids	PTFE
Shell 4 ball (IP239)(ASTM D 2596)	
Weld load	315kg
Scar diameter	0.36mm (40kg for 1 hour)
Scar diameter	0.56mm (60kg for 15 mins)
Storage	Storage temperature should be kept below 50 °C. Storage area should be: out of direct sunlight.
Pack sizes	400ml

Issue 34341c: Jan-04

2

### **ROCOL Lubricants**

ROCOL House, Swillington, Leeds LS26 8BS, England.

Tel: +44 (0)113 232 2600 Fax: +44 (0)113 232 2760

[www.rocol.com](http://www.rocol.com)

ROCOL is a BS EN ISO 9001 registered company.

ROCOL is a trade mark of ITW Inc.

The information in this publication is based on our experience and reports from customers. There are many factors outside our control or knowledge which affect the use and performance of our products, for which reason it is given without responsibility.

TECHNICAL DATA